



TOUAREG

Water-based metallic and pearlescent decorative finish
INTERIOR



DESCRIPTION

TOUAREG is a water-based acrylic copolymer decorative effect finish.

FIELD OF USE

Recommande for interior walls.

TECHNICAL CHARACTERISTICS

- Aspect : Coloured, slightly Metallic and Pearlescent effect.
- Colours : See our catalogue.
- Spreading-rate : About 6 m²/L (in 2 coats), complies with ISO 23811 (2009).
- Density : 1.07 Kg/L +/- 0.05 depending upon the colour to 25° C, complies with NM ISO2811-1(2008).
- Viscosity : 108 KU's +/- 10 @ 25° C, complies with ASTM D561 (1991).

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with a Chiendent brush.
- * Sand with sandpaper.
- * Remove the dust.
- * Wash with a water-jet if necessary.

APPLICATION PROPERTIES

Using a roller, apply an even coat of Fondo ATF (White) or Colofondo (Tinted) over the surface. Let the Colofondo dry for 12 hours.

Using the special short pile roller, apply Touareg (diluted with 20% of water) in all directions over the surface. To reduce the risk of lapping problems, work in areas of 1 to 2 m².

Leave the product to dry.before applying a second diluted coat (and if necessary a third coat) using the short pile roller. Using a blade or rendering tool, spread out the Touareg in order to obtain the special effect. Do not apply on cold wet walls below 5°C or conditions of high relative humidity (> 70%).

APPLICATION DETAILS FOR USAGE

Dilution : This product is ready for application. Mix well before use. Depending upon the application method used, this product can be diluted with upto 20% of tap water.

DRYING TIME

Drying time at 20°C and 60% relative humidity:

- *Touch dry : 3 to 4 hours.
- *Dry : 24 hours.
- *Washable : 20 days.

RECOMMENDED SYSTEM (consult us)

■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM	1
COLENDUIT EXTRA B505 ou SP88	2
COLOVINYL 600	1
COLOFONDO	1
TOUAREG	1

STORAGE

Two years in the closed plastic container, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures.

PACKAGING

- *TOUAREG : 2 Liters.
- *COLOFONDO : 1,6 liters.
- * FONDO : 4 kg (Spreading-rate 6 to 7m²/kg).

HEALTH & SAFETY

This product is not classified as dangerous under current regulations.

Fore more details, consult the safety data sheet N° 65.

Edition : October 2016 by Colorado (10/16).
This version replaces all previous editions.

N.B : The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

COLORADO is certified ISO 9001, ISO 14001 & OHSAS 18001